



ELCA
QUALITY SYSTEMS & CALIBRATIONS PVT. LTD.

Plot No. S-152, S Block, Indrayani Nagar Road, MIDC, Bhosari, Pune - 411026. INDIA.
 Tel : 020-68191111 E-MAIL : qc@elcalabs.com WEB : www.elcalabs.com



TC - 5744


HUMIDITY TEST

ELCA Report No: A/23/7699/P


Date :06.05.2023

Test Method : ASTM D 2247 (2015 RA 2021)

Annexure 1



(BEFORE HRS)



(AFTER 96 HRS)

Checked By
Mohini Chavan

Authorized Signatory

Mr. Vidyanand Galphade
Dy. General Manager

1. This report relates only to the sample(s) submitted and tested. 2. Sample(s) are submitted by the customer and not drawn by ELCA QUALITY SYSTEMS & CALIBRATIONS PVT. LTD. 3. Report shall not be reproduced, except in full without prior written permission of ELCA QUALITY SYSTEMS & CALIBRATIONS PVT. LTD. 4. Any correction to report without authorization invalidates report. 5. The details documented in the "Sample Description" are as provided by the customer in their challan/letter/Test Request. 6. While ELCA has made best endeavors to provide accurate and reliable information, liability of ELCA is limited to the value of the testing charges billed for the respective sample and ELCA is not responsible for any financial liability due to any act of omission or error. (Others Terms & Conditions Overleaf)
 Format : EQC/7.8/1



ELCA QUALITY SYSTEMS & CALIBRATIONS PVT. LTD.

Plot No. S-152, S Block, Indrayani Nagar Road, MIDC, Bhosari, Pune - 411026. INDIA.
Tel : 020-68191111 E-MAIL : qc@elcalabs.com WEB : www.elcalabs.com



TC - 5744

TEST REPORT

Page 1 of 1

Customer: M/s. RUSTCHEM CORROSOLS PRIVATE LIMITED PLOT NO V 99, CHAKAN MIDC PHASE 2, NEAR GENERAL ELECTRIC LTD, WASULI, PUNE 410501	Report No.:	A-23-7699-P
	Report Date:	06-05-2023
	Job. No.:	ELP-22-23-32863
	Sample Received Date:	30-04-2023
	Date Of Completion:	06-05-2023
	ULR No.:	TC574423000019502F

Customer Ref. No. & Date: 0065/2023-24 30-04-2023

Samples not drawn by ELCA

Product Specification: --

Sample Description: Test Sample, Make: Rustchem

HUMIDITY TEST

Discipline	Chemical	Group	PAINT & SURFACE COATING
Test Method :	ASTM B117:2019		
Tested At	ELCA Quality System Pune	Tested on :	06-05-2023

Parameter	Result
Loading Date	02.05.2023
Unloading Date	06.05.2023
Protection Used	Not used
Method Of Supporting	Nylon thread
Temperature within Exposure zone	38.6 to 39.4°C
Exposure Period	96 Hours
Realitive Humidity	90 to 94%
Type of Water	Distilled water
Method of Cleaning	Running Water
No of Hours	-
96	No rust observed.

Remark: Annexure Attached

*****END OF REPORT*****

Checked By
Mohini Chavan

Authorised Signatory
Mr. Vidyanand Galphade
Dy. General Manager

